

WEARTECH® SHS™ 9192U

Severe Abrasion, Flux-Cored (FCAW-S) Wire

Application Process

FCAW-S/GMAW-C

Weld Overlay for Hardfacing

Material Chemistry (wt%)

Chromium	< 20%
Molybdenum	< 10%
Niobium	< 10%
Tungsten	< 10%
Aluminum	< 5%
Boron	< 5%
Carbon	< 5%
Manganese	< 5%
Silicon	< 2%
Iron	Balance

Rockwell C (HRC) Hardness

69 - 72 HRC Typical

Wear Resistance

ASTM G65-04 Procedure A

Typical mass lost of 0.10g

Weld Deposit Properties

Density (g/cm³) 7.68

Impact Resistance

Drop Impact Testing:

Passed multiple impacts at
165 ft-lbs

Overlay Description

SHS9192U is an iron based steel alloy with a near nanoscale (submicron) microstructure that features extreme abrasion resistance with high toughness, high volume of hard phases and superior high temperature hardness. SHS9192U is an alternative to chrome and tungsten carbides.

Key Performance Characteristics

- 69 - 72 HRC single and double pass weld deposits
- Extreme resistance to abrasion while maintaining high toughness
- Alternative weld material to:
 - Tungsten carbides
 - Chrome carbides
 - Complex carbides
 - Stick weld material loaded with carbides
 - Tungsten carbide laden Teflon® sheet overlays
- Maintains high hardness after exposure to high temperatures

SHS9192U represents a breakthrough in the development of hardfacing wires due to its ability to survive in extreme environments. SHS9192U is a patented multicomponent, glass-forming iron-based steel alloy designed to replace and be superior to existing cored wire products including chrome carbide, complex carbides and tungsten carbides; stick weld material loaded with carbides; and tungsten carbide laden Teflon® sheet overlays traditionally used for high abrasion environments. When applied as a weld overlay, SHS9192U deposits provide extreme resistance to abrasion while maintaining high toughness. While conventional weld overlay materials are macrocomposites containing hard particles and general carbides in a binder, SHS9192U is unique since it starts with a uniform glass-forming melt chemistry which allows high undercooling to be achieved during welding. This results in considerable refinement of the microstructure down to the micron and submicron range.



Extreme Abrasion Resistance

SHS9192U exhibits extreme abrasion resistance through the in situ formation of high volume fractions (i.e. 60% - 70%) of complex borocarbide phases. Conventional approaches to wire design incorporate hard particles in the core of the wire and are limited volumetrically to much lower fractions of hard particles which limit their wear performance. In wear resistance testing, typical mass loss of 0.10g in ASTM G65-04 abrasion tests for SHS9192U is revolutionary in a weld wire product. This unmatched wear performance allows SHS9192U to be used as an alternative for some severe wear applications currently dominated by 60% tungsten carbide PAW materials, the previous benchmark weld material for wear performance.

Industrial Uses

Mining

Structure



400mm length, near nanoscale microstructure

WEARTECH[®] SHS[™] 9192U

Severe Abrasion, Flux-Cored (FCAW-S) Wire

Single Pass Hardness/Wear Resistance

SHS9192U has been engineered so that while the same levels of dilution can be expected (~ 30%) based on the application method, the dilution layer itself retains maximum hardness and wear resistance after a short distance from the weld overlay interface (i.e. within 100 μm). This allows maximum hardness/wear resistance to develop in the first weld overlay pass while conventional weld materials need two or more passes to generate their best wear characteristics. Elevated temperature hardness measurements have shown 680 Vickers hardness (60 HRC) is maintained at 1100 °F showing that SHS9192U exhibits superior elevated temperature hardness. SHS 9192U overlays should be limited to two layers for typical applications

High Deposition Rate

SHS9192U does not rely on the incorporation of hard particles in the interior of the sheath, but instead high volume fractions of borocarbide phases form in situ during welding. This allows high amperage and wire feed rates to be used during the weld overlay process. Competing tungsten carbide wire materials often specify much lower feed rates due to carbide breakdown and dissolution which limits deposition rate and increases costs.


Superior Combinations of Wear Resistance and Toughness

Superior wear resistance of SHS9192U occurs from the in situ formation of high volume fraction of refined complex borocarbide phases. The borocarbide phases, which form during solidification, are completely wetted by the matrix and prevent premature pull-out delamination and crack nucleation. The refined nature of the borocarbide phases allows the reduction of stress concentration sites and the ductile matrix, which consists of α -Fe and α -Fe phases, supplies effective crack blunting and bridging.

Hardness as a Function of Heat Treatment


The effect of exposure to elevated temperature for SHS9192U and SHS9700U wires can be seen in the figure to the right. SHS9192U retains its hardness very well through temperatures of 1,000 °F with only a small drop from the as welded hardness. SHS9700U shows a larger drop initial drop in hardness but it then stays above 61 HRC through 1,000 °F.

HRC Hardness



Properties such as hardness are developed within microns of the weld interface

Hardness After Heat Treatment



High hardness is retained after exposure to elevated temperatures

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.

WEARTECH® SHS® 9192U

Severe Abrasion

KEY FEATURES

- Extreme resistance to abrasion
- Maintains high hardness after exposure to high temperatures
- Provides exceptional uniformity of hardness and wear performance across a range of service environments
- Limited to 2 layers max

TYPICAL APPLICATIONS

- Wearplate
- Ore Chutes
- Crusher Rolls
- Screw Augers

Diameter in (mm)	25 lb (11.3 kg) Spool PLW	30 lb (13.6 kg) Spool PLW	55 lb (25 kg) Coil
0.045 (1.1)	W9192-120X15 (ED035663*)	W9192-160X15 (ED035662*)	W9192-240X25 (ED035661*) W9192-280X25 (ED035660*)
1/16 (1.6)			
3/32 (2.4)			
7/64 (2.8)			

* EDO numbers have been discontinued and replaced by the Wearthech part numbers for the cross selling program.

MECHANICAL PROPERTIES⁽¹⁾

Rockwell Hardness (R _c)	Wear Resistance
69-72	ASTM G65-04 Procedure A, 0.10 g mass loss

DEPOSIT COMPOSITION⁽¹⁾

%Fe	%C	%Cr	%W	%B	%Mo	%Nb	%Mn	%Si	%Al
Balance	<5	<20	<10	<5	<10	<10	<5	<2	<5

TYPICAL OPERATING PROCEDURES

Diameter, Polarity ESO - in (mm)	Current (Amps)	Voltage (Volts)	Wire Feed Speed m/min (ipm)	Shielding Gas	Flow Rate (cfh)
0.045 in (1.1mm), DC+ ½ - ¾ (15) GMAW-C ¾ - 1 (20) FCAW-S	~135	24	7.0 (275)	75 Ar - 25 CO ₂	35 - 45
1/16 in (1.6mm), DC+ ½ - ¾ (15) GMAW-C ¾ - 1 (20) FCAW-S	~220	24	7.0 (275)	75 Ar - 25 CO ₂	45 - 60
3/32 in (2.4mm), DC+ ¾ - 1 (20) GMAW-C ¾ - 1.25 (25) FCAW-S	~375	25	7.0 (275)	75 Ar - 25 CO ₂	55 - 70
7/64 in (2.8mm), DC+ ¾ - 1 (20) GMAW-C 1 - 1¾ (40) FCAW-S	~450	26	5.7 (225)	75 Ar - 25 CO ₂	60 - 80

⁽¹⁾ Composition and properties depend upon dilution. Single layer deposit properties depend upon base metal and/or build-up material.

<p>IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED</p> <p>Fumes from the normal use of some welding products can contain significant quantities of components - such as chromium and manganese - which can lower the 5.0 mg/m³ maximum exposure guideline for general welding fume.</p> <p>BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.</p>

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.