

# WEARTECH® SHS™ 9700E

Severe Abrasion, Stick (SMAW) Electrode

## Application Process

SMAW Weld Overlay for  
Hardfacing

## Material Chemistry (wt%)

Chromium	< 18%
Niobium	< 10%
Boron	< 6%
Aluminum	< 5%
Potassium Silicate	< 5%
Carbon	< 3%
Manganese	< 2%
Silicon	< 2%
Iron	Balance

## Rockwell C (HRC) Hardness

67 - 70 HRC

## Wear Resistance

ASTM G65-04 Procedure A  
Typical mass loss of 0.13g

## Weld Deposit Properties

Density (g/cm<sup>3</sup>) 7.36

## Impact Resistance

Drop Impact Testing:  
Passed multiple impacts  
at 165 ft-lbs

## Overlay Description

SHS9700E Stick Electrode is an iron based steel alloy with a near nanoscale (submicron) microstructure that features exceptional abrasive wear resistance with superior toughness and no high-cost nickel, tungsten and molybdenum in material chemistry. SHS9700E has been designed to be deposited on mild and low alloy steels.

## Key Performance Characteristics

- 67 - 70 HRC single and double pass weld deposits
- Cost effective alternative to complex carbides: iron-based chemistry contains no tungsten, no molybdenum and no nickel
- Provides exceptional wear resistance lasting significantly longer than most chrome carbide and complex carbide alloys
- High resistance to abrasion while maintaining high toughness
- Crystalline microstructure is engineered to submicron (400 nm) size
- Maintains high hardness after exposure to elevated temperatures

SHS9700E is a multicomponent steel alloy with a unique uniform glass-forming melt chemistry that allows high undercooling to be achieved during welding. This results in considerable refinement of the crystalline microstructure down to a near nanosize (submicron) range. Unlike conventional weld overlay materials which are macrocomposites containing hard particles and general carbides in a binder, the refined microstructure of SHS9700E is a uniformly hard matrix when welded and does not incorporate distinct hard particles in a binder. This allows SHS9700E to provide vastly improved hardness and wear resistance, and to significantly outlast conventional macrocomposites. Additionally, SHS9700E is an iron-based alloy without tungsten carbide particulates.

## High Hardness

Near maximum hardness is achieved in both single and double layer overlays with SHS9700E when overlaying mild steel or low alloy iron based materials. The alloys have been designed such that the greater base metal dilution present in a single layer overlay does not cause a significant reduction in hardness.


## High Wear Resistance

SHS9700E weld deposits should be limited to two layers maximum for most applications. Both single and double layers provide exceptional wear resistance of typical 0.13g mass loss in ASTM G65-04 dry sand rubber wheel abrasion tests.

## Industrial Uses

Mining

## Microstructure



SHS9700E features a near nanoscale microstructure with grain sizes less than 400 nm

# WEARTECH® SHS™ 9700E

Severe Abrasion, Stick (SMAW) Electrode

## Damage Tolerance

The superior toughness of SHS9700E occurs from the in-situ formation of high-volume fraction of refined complex borocarbide phases during welding which are surrounded by ductile phases. The borocarbide phases, which form during solidification, are completely wetted by the matrix and prevent premature pull-out, delamination and crack nucleation. The refined nature of the borocarbide phases allows the reduction of stress concentration sites and the ductile matrix supplies effective crack blunting and bridging.

## Weld Characteristics

SHS9700E welds with a smooth stable transfer when applied with the recommended parameters. It is best to maintain a moderate arc length to minimize shorting of the arc to the silica slag that floats in the weld pool. Weld deposits have a smooth surface texture with minimal slag spots that can be removed with a chipping hammer or needle gun.

## Substrate Compatibility

SHS9700E has been designed for overlay applications on mild and low alloy steels.

SHS9700E is not suitable for overlay applications on cast irons, manganese steels, austenitic stainless alloys or can we put on one line non iron based materials such as nickel or cobalt based alloys.

#### CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.

# WEARTECH® SHS® 9700E

Severe Abrasion

## KEY FEATURES

- Lower cost while maintaining a near nanoscale (submicron) microstructure
- Provides exceptional wear resistance lasting significantly longer than most chrome carbide and complex carbide alloys
- Maintains high hardness after exposure to elevated temperatures
- Limited to 2 layers max

## TYPICAL APPLICATIONS

- Wearplate
- Crusher rolls
- Ore Chutes
- Screw augers

## WELDING POSITIONS

Flat & Horizontal

## DIAMETERS / PACKAGING

Diameter in (mm)	10 lb (4.5 kg) Carton
5/32 (4.0)	E9700-400X350 (ED035669*)

\* EDO numbers have been discontinued and replaced by the Wearthech part numbers for the cross selling program.

## MECHANICAL PROPERTIES<sup>(1)</sup>

Rockwell Hardness (R <sub>c</sub> )	Wear Resistance
67-70	ASTM G65-04 Procedure A 0.13 g mass loss

## DEPOSIT COMPOSITION<sup>(1)</sup>

	%Fe	%C	%Cr	%B
Requirements	Balance	<3	<18	<6
	%Nb	%Al	%Mn	%Si
Requirements	<10	<5	<2	<2

## TYPICAL OPERATING PROCEDURES

Diameter, Polarity in (mm)	Current (Amps)
5/32 in (4.0mm), DC+	150-175

<sup>(1)</sup>Composition and properties depend upon dilution. Single layer deposit properties depend upon base metal and/or build-up material.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED

Fumes from the normal use of some welding products can contain significant quantities of components - such as chromium and manganese - which can lower the 5.0 mg/m<sup>3</sup> maximum exposure guideline for general welding fume.

BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

*Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at [www.lincolnelectric.com](http://www.lincolnelectric.com)*

#### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

#### CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.